

Same Day Sealer
Wet Look Appearance, High Solids



Characteristics & Technical Data

% Solids by Weight (+/- 3%):	40%
QUV (ASTM D G-54):	2,000 hours with no gloss loss
WT./Gal	8.77 lbs.
Coverage:	200-300 SqFt/Gal @ 3mil DFT
Pot Life:	2 Hours
VOCs:	<125 G/L

4. Properties & Special Features

- Contractor grade, water based wet look sealer
- Pressure clean and seal in the same day.
- Helps locks down paver joint sand.
- Helps inhibits mold, weeds and ant hills.
- Catalyzed product that resists gas and oil.

5. Directions

Before You Begin: Surfaces must be clean and free of any contaminants before sealing. SDS performance is directly related to how thoroughly the surfaced is prepared. Do not apply when the temperature of the air or the surface to be coated is below 50°F. Testing on your surface is always recommended to ensure desired results.

Surface Preparation: Pavers must be clean and free of efflorescence. Scrape and remove all loose material prior to application. Cobble Clean, Cobble Prep and Cobble Oxhide may be used for specific cleaning situations.

Mixing Instructions: SDS is a two component kit. Part A must be mixed with Part B. A 5 gallon kit includes a short filled 5 gallon pail and a one gallon pail of Part B. Part A and Part B must be mechanically mixed with a power mixer (drill mixed) for a minimum of 2 - 5 minutes. For application dilute mixed SDS with one part water and one part mixed sealer in a 1:1 ratio. Drill mix for 2-5 minutes.

Applications

Roller: Apply with a 3/8" to 3/4" nap roller cover. Avoid over rolling. Always maintain a wet edge.

Continued ->

1. Manufacturer

SurfaceLogix – a Reliance Supply Company
1880 NW 18th Street
Pompano Beach, FL 33069

Phone: 954.971.9111
Fax: 954.971.6623
Email: support@surfacelogix.net
surfacelogix.net

2. Product Description

Same Day Sealer is our contractor grade solution using the newest technology in waterborne protection for brick paver. Same Day Sealer is low VOC with the “wet look” of our original paver sealer Cobble Coat. SDS also helps to inhibit weed growth and ant hills. SDS is very tolerant to moisture, so in most cases cleaning and sealing can be done in the same day.

3. Applications

Use SDS anywhere that **pavers** require protection from the sun or staining.

SDS is not recommended for pavers installed over a solid surface or on surfaces where moisture is unable to dissipate.



Clear Sealers: COBBLE LOC, 131-1g, 131-5g

Technical Data Sheet

SAME DAY SEALER

Wet Look Appearance, High Solids

5. Directions (Continued)

Airless Sprayer: Spray by overlapping each pass. Always apply in an even film deposit and maintain a working wet line.

On Bare Surface: One and sometimes two thin coats (2 dry mils) provide the best results on uncoated surfaces.

Over Previously Sealed: One coat is recommended.

6. Packaging

Size	Package	Per Case	Units / Pallet
1 gallon kit	Pail	4	148
5 gallon kit	Pail	N/A	36

9 pounds per 1 gallon pail, 45 pounds per 5 gallon pail

7. Coverage

1 gallon covers 200 to 300 square feet per coat. Coverage will depend on surface porosity, joint width and application method. Second coat will take slightly less product.

8. Curing Information

Dry To Touch: 2 to 6 Hours (varies with conditions)

Recoat: 2 to 6 hours

Full Cure: 48 to 72 Hours

9. Storage & Shelf Life

Product must be kept in its original, unopened and tightly sealed container. Store in a dry and well ventilated place with controlled temperature (50°F to 90°F). Keep sheltered from weather and direct sunlight. In proper storage conditions, the product's shelf life is 12 months following production (see date on packaging). Store product in original container and close lid tightly after each use.

10. Maintenance

Cobble Clean is recommended for routine cleaning. Follow Cobble Clean instructions for dilution ratios.

11. Shipping

Land & Sea: Not Regulated

Packing Group: III

Flash Point: 116F

12. Clean Up

Clean sprayer and tools with water and SurfaceLogix Reducer immediately after use. Flush water through the line of the sprayer until clear. Leave SurfaceLogix Reducer in the line of machine after flushing with water.

13. Health Hazard Information

Eye Contact: Wear eye protection. May irritate eyes. If in eyes, flush with water for at least 15 minutes.

Inhalation: Use a NIOSH approved respirator.

Ingestion: If swallowed, DO NOT induce vomiting. Seek medical attention.

Skin: Avoid prolonged contact with skin.

Use with adequate ventilation.

Coated surfaces may become slippery. SurfaceLogix non-skid additive should be incorporated in this situation. It is the sole responsibility of the applicator to determine whether a non-skid additive is appropriate for the job.

14. Technical Support

For friendly, knowledgeable and courteous technical support please call 954.971.9111.

You may also reach us by sending a query from our website at www.surfacelogix.net.

15. Disclaimer

All SurfaceLogix products are manufactured with the finest raw materials. It is the applicator's responsibility to determine the appropriate use of the product.

All recommendations and suggestions are made without guarantee, since conditions of use are beyond our control.