

COBBLE IMPREGNATOR (NS)

Natural Look Appearance, No Sheen



Characteristics & Technical Data

% Solids by Weight (+/- 3 %):	17%
QUV (ASTM D G-54):	2,000 hours with no protection loss
WT./Gal	8.5 lbs.
Coverage:	200-300 SqFt/Gal @ 3mil DFT
VOCs:	>59 G/L

4. Properties & Special Features

- Eco friendly & emits low VOC's.
- Easy to apply.
- Excellent stain resistance.
- Breathable.

1. Manufacturer

SurfaceLogix – a Reliance Supply Company
1880 NW 18th Street
Pompano Beach, FL 33069

Phone: 954.971.9111
Fax: 954.971.6623
Email: support@surfacelogix.net

www.surfacelogix.net

2. Product Description

Clear protector for natural stone & clay pavers. Protects against staining, water and sun damage. This low VOC water based formula will leave the substrates natural look with a breathable, and stain resistant finish.

3. Applications

Use Cobble Impregnator (NS) penetrating sealer to achieve no surface film on driveways, pool decks, public entryways, walkways, median strips, and patios constructed of:

Natural Stone • Clay Pavers

5. Directions

Before you begin: Surfaces must be clean and free of any contaminants before sealing. Cobble Impregnator (NS)'s performance is directly related to how thoroughly the surfaced is prepared. Do not apply when the temperature of the air or the surface to be coated is below 50°F. Testing on your surface is always recommended to ensure desired results.

Surface Preparation: Read label instructions carefully. Cobble Clean, Cobble Prep & Cobble Oxhide may be used for specific cleaning situations. One uniform coat should provide the best results. Remove excessive or puddle product from the surface within 15 minutes.

Mixing Instructions: Stir product.

Applications

Roller: Apply with a 3/8" to 3/4" nap roller cover. Avoid over rolling. Always maintain a wet edge.

Airless Sprayer: Spray by overlapping each pass. Always apply in an even film deposit and maintain a working wet line.

On Bare Surface: One coat provides the best results. If necessary to recoat, do so while coat is still wet.

Continued ->

surfacelogix

CHEMISTRY THAT PROTECTS YOUR WORLD

Clear Sealers: COBBLE IMPREGNATOR (NS), 134-1g, 134-5g

Technical Data Sheet

COBBLE IMPREGNATOR (NS)

Natural Look Appearance, No Sheen



5. Directions (Continued)

Over Previously Sealed: Film forming sealers will need to be stripped prior to application. Cobble Impregnator (NS) may be applied over non film forming sealers provided the prior application is sufficiently worn away.

6. Packaging

Size	Package	Per Case	Units / Pallet
1 gallon kit	Pail	4	148
5 gallon kit	Pail	N/A	36

9 pounds per 1 gallon pail, 45 pounds per 5 gallon pail

7. Coverage

1 gallon covers 200 to 300 square feet per coat. Coverage will depend on surface porosity, joint width and method of application. Natural Stone may require less material than other substrates.

8. Curing Information

Dry To Touch: 30 Minutes

Recoat: If necessary recoat while first coat is still wet. Once dry Cobble Impregnator (NS) will not accept an additional coat of the product.

Full Cure: 48 to 72 Hours

9. Packaging

Product must be kept in its original, unopened and tightly sealed container. Store in a dry and well ventilated place with controlled temperature (50°F to 90°F). Keep sheltered from weather and direct sunlight. In proper storage conditions, the product's shelf life is 12 months following production (see date on packaging). Store product in original container and close lid tightly after each use.

10. Maintenance

Cobble Clean is recommended for routine cleaning. Follow Cobble Clean instructions for dilution ratios.

11. Shipping

Land & Sea: Not Regulated

Packing Group: III

Flash Point: Not Applicable

12. Clean Up

Clean sprayer and application tools with water.

13. Health Hazard Information

Eye Contact: Wear Eye Protection. May irritate eyes. If in eyes, flush with water for at least 15 minutes.

Inhalation: Use a NIOSH approved respirator.

Ingestion: If swallowed, DO NOT induce vomiting. Seek medical attention.

Skin: Avoid prolonged contact with skin.

Use with adequate ventilation.

Any surface may become more slippery when a coating is applied. In testing, Cobble Enhancer increased the coefficient of friction on many substrates IE did not make the surface more slippery.

14. Technical Support

For friendly, knowledgeable and courteous technical support please call 954.971.9111.

You may also reach us by sending a query from our website at www.surfacelogix.net.

15. Disclaimer

All SurfaceLogix products are manufactured with the finest raw materials. It is the applicator's responsibility to determine the appropriate use of the product.

All recommendations and suggestions are made without guarantee, since conditions of use are beyond our control.