



Decking: **TD One Step**, 115-1g, 115-5g

Technical Data Sheet

TD ONE STEP

Concrete Resurfacing Deck System

Characteristics & Technical Data

| | |
|------------------------------|---|
| % Solids by Weight (+/- 3%): | 48% |
| Appearance | Pancake batter |
| WT./Gal | 12 lbs. |
| Coverage: | Rolled - 75 to 100 SqFt/Gal Hopper Sprayed - 150 to 200 SqFt/Gal |
| Clean Up: | Water |
| VOCs: | 160 G/L |

4. Applications

- Decking surface for patios, driveways, catwalks, and walkways
- Schools, hotels and public spaces
- May be used over sound asphalt
- Topping for new concrete or protection and beautification of old concrete
- Topping for previously decked finishes for refreshing and beautification
- Ramps and other surfaces where non-skid is needed

5. Directions

Before you begin: Surfaces must be clean and free of any contaminants before sealing. TD One Step's performance is directly related to how thoroughly the surfaced is prepared. Do not apply when the temperature of the air or the surface to be coated is below 50°F. Testing on your surface is always recommended to ensure desired results.

Surface Preparation: Smooth concrete must be acid etched with a muriatic acid blend (1 part acid to 3 parts water) so as the concrete feels rough to the touch like 120 to 200 grit sand paper. Scrape and sand all loose material prior to application. Cobble Clean and Cobble Prep may be used for specific cleaning situations. After pressure cleaning, surface must be allowed 24 hours to dry prior to application.

Directions: Stir TD One Step prior to use; a paddle mixer will work best. Roll out first coat with a 3/4" to 1" nap roller in a uniform coat approximately 75 to 100 feet per gallon. If multiple colors are desired, allow to dry 3 hours then splatter 2nd and 3rd color with a hopper gun sprayer. On commercial applications and driveways apply a coat of SurfaceLogix Cobble Coat H2O clear sealer or Cobble Loc the next day for extra protection.

Cleaning Tools: Use water

1. Manufacturer

SurfaceLogix – a Reliance Supply Company
 1880 NW 18th Street
 Pompano Beach, FL 33069

Phone: 954.971.9111
 Fax: 954.971.6623
 Email: support@surfacelogix.net
 www.surfacelogix.net

2. Product Description

Texture Deck One Step (TD One Step) is the latest technology in a non-slip decorative, 100% acrylic textured deck system. Now you don't have to mix two component materials. TD One Step is ready to go right out of the bucket. Enjoy the same hard finish as our Texture Deck system with the ability to roll and hopper spray a variety of patterns.

3. Properties & Special Features

- One component product, no mixing
- No pot life, no waste
- Color consistency
- Environmentally friendly
- Quick to work with, saves time and labor
- Roll or hopper spray a variety of patterns
- Adds strength to concrete surfaces

surfacelogix

CHEMISTRY THAT PROTECTS YOUR WORLD

Decking: TD One Step, 115-1g, 115-5g

Technical Data Sheet

TD ONE STEP

Concrete Resurfacing Deck Mix



6. Packaging

| Size | Package | Per Case | Units / Pallet |
|----------|---------|----------|----------------|
| 1 gallon | Pail | 4 | 144 |
| 5 gallon | Pail | N/A | 36 |

12 pounds per 1 gallon pail, 60 pounds per 5 gallon pail

7. Coverage

1 gal. covers 75-100 square feet when troweled and 150-200 when hopper sprayed.

8. Curing Information

Dry to touch and recoat: 1 hour
Recoat : 3 hours
Full cure: 72 hours

Do not apply TD One Step when air or surface temperatures are below 50°F or are expected to fall to that point before application is cured. Low temperatures and high humidity can extend drying and curing times.

9. Storage & Shelf Life

Product must be kept in its original, unopened and tightly sealed container, and stored in a dry and well ventilated place with controlled temperature (50°F to 90°F). Keep sheltered from weather and direct sunlight. In proper storage conditions, the product's shelf life is 12 months following production (see date on packaging). Store product in original container and close lid tightly after each use.

10. Maintenance

Cobble Clean is recommended for routine cleaning. Follow Cobble Clean instructions for dilution ratios.

11. Shipping

Land and sea: NOT REGULATED
Packing Group: III
Flash Point: NA

12. Clean Up

Clean equipment and tools with soap and water immediately after use.

13. Health Hazard Information

Eye Contact: Wear Eye Protection. May irritate eyes. If in eyes, flush with water for at least 15 minutes.
Inhalation: Use a NIOSH approved respirator.
Ingestion: If swallowed, DO NOT induce vomiting. Seek medical attention.
Skin: Avoid prolonged contact with skin.

New concrete should be cured for a minimum of 24 days. It is always recommended when going over another coating system to apply a test area to insure proper adhesion.

14. Technical Support

For friendly, knowledgeable and courteous technical support please call 954.971.9111.

You may also reach us by sending a query from our website at www.surfacelogix.net.

15. Disclaimer

All SurfaceLogix products are manufactured with the finest raw materials. It is the applicator's responsibility to determine the appropriate use of the product.

All recommendations and suggestions are made without guarantee, since conditions of use are beyond our control.